



## SPECIFICATIONS

### Nyacol® colloidal silica

<b>830</b>	Viscosity, cps	6-13
	% SiO <sub>2</sub>	28.3-31.6
	% Na <sub>2</sub> O	0.48-0.62
	pH	9.8-11.2
	Specific Gravity	1.200-1.230
<b>1430</b>	Viscosity, cps	4-12
	% SiO <sub>2</sub>	29.0-31.0
	% Na <sub>2</sub> O	0.33-0.47
	pH	9.6-11.0
	Specific Gravity	1.200-1.216
<b>1440</b>	Viscosity, cps	<26
	% SiO <sub>2</sub>	38.7-41.3
	% Na <sub>2</sub> O	0.38-0.59
	pH	9.7-11.1
	Specific Gravity	1.279-1.321

Origin date:  
Revision date:

April 9, 1998

®Nyacol is a registered trademark of the PQ Corporation.

**R&R®**  
**DENSPLY®**

EUROPEAN AGENT:

**HTM Tradeco Ltd.**  
Phone: 208/4434323 (UK)  
Fax: 208/8040127 (UK)

**Ransom & Randolph**

3535 Briarfield Blvd.  
Maumee, OH 43537 USA  
**USA Phone: (800)800-7496**  
Phone: (419)865-9497  
FAX: (419)865-9997  
[www.ransom-randolph.com](http://www.ransom-randolph.com)