

# R&R® WASH-N-ETCH

pattern cleaner concentrate

R&R Wash-N-Etch pattern cleaner removes silicone oil or other release agents from wax patterns before the primary ceramic coat is applied. R&R Wash-N-Etch is a biodegradable, completely safe product for cleaning wax patterns. R&R Wash-N-Etch contains naturally occurring d-limonene, derived from citrus fruits, as the active ingredient.

R&R Wash-N-Etch also acts as an etching material for the wax pattern while it cleans off the release agent. This process allows for better slurry adhesion during application of primary coats. Better adhesion of the primary coats reduces opportunities for casting defects related to shell buckling or lifting.

## **APPLICATION RECOMMENDATIONS**

Patterns cleaned in R&R Wash-N-Etch can be dipped in water based primary slurries after they have dried.

After the wax patterns are cleaned and rinsed with water, an acclimation period of at least one hour is recommended in the primary slurry area of the shell room to ensure wax patterns are not expanding or contracting from changes in temperature.

R&R Wash-N-Etch can be used full strength as packaged for difficult to release patterns that require a heavy coat of release agent. It may also be used full strength for patterns that have difficult part geometry.

R&R Wash-N-Etch can be diluted to 75% concentration for normal use, making it more economical to use.

## **TYPICAL PROCESS RECOMMENDATION**

1. Agitated immersion in R&R Wash-N-Etch for 30 seconds.

NOTE: This may vary depending on part geometry or amount of silicone to be removed.

2. Agitated immersion in room temperature water for 15 seconds in an overflow tank.

3. Agitated immersion in room temperature water for 15 seconds in a second overflow tank.

Depending on state EPA guidelines, overflow water rinse tanks may be arranged so that the second tank overflows into the first and the first overflows into a drain. Consult your local EPA before pouring liquids down the drain.

Perforated tubing or piping may be added to the bottom of the water rinse tanks. By pumping air through these lines during the rinse process, agitation will be enhanced.



**R&R**  
**DENSPLY**

**EUROPEAN AGENT:**

**HTM Tradeco Ltd.**

Phone: 208/4434323 (UK)

Fax: 208/8040127 (UK)

htmtradecoltd@aol.com

**Ransom & Randolph**

3535 Briarfield Blvd.

Maumee, OH 43537 USA

**USA Phone: (800)800-7496**

Phone: (419)865-9497

FAX: (419)865-9997

www.ransom-randolph.com

## **RECOMMENDED TESTING METHODS**

Given the number of variables introduced into a cleaning tank (i.e. release agent variance, wax variance, volume variance), determining product life and product performance can be difficult. As a result, we recommend implementing a regular monitoring schedule on each cleaning tank.

The following tests can assist with monitoring the effectiveness of the cleaning material:

### 1. Wetting Test.

Dip a clean wax bar or pattern into primary binder prewet to its mid-point.

Remove from binder and observe the surface.

Good wetting indicators: uniform coat, no slurry breaks

Poor wetting indicators: wax peeks through the slurry coat, slurry breaks and forms holes

### 2. Styrofoam Cup Dissolution Test

Pour pattern cleaner into styrofoam cup.

Set styrofoam cup in a pan.

Record number of minutes it takes for cleaner to dissolve through cup.

NOTE: Baseline must be recorded with pattern cleaner before it is used in production. Test should be repeated using same size cup for accurate comparison. Record time at which the cleaner seeps through the styrofoam cup for consistent measure.

Record on regular basis. We would anticipate it will take longer to dissolve the cup over the effective life of the cleaner.

Historical record will allow for correlation of dissolution time with loss of effectiveness.

## **TYPICAL PROPERTIES**

Appearance:	pale, yellow liquid (Product darkens with age. This is not an indicator of performance capability.)
Odor:	citrus
pH:	9.0 - 10.0
VOC (EPA-24):	3.5 lbs/gal (as received)

## **SAFETY & HANDLING**

Consult Material Safety Data Sheet (MSDS) for safety and handling recommendations.



**R&R**  
**DENTSPLY**

**EUROPEAN AGENT:**

**HTM Tradeco Ltd.**  
Phone: 208/4434323 (UK)  
Fax: 208/8040127 (UK)  
htmtradecold@aol.com

**Ransom & Randolph**

3535 Briarfield Blvd.  
Maumee, OH 43537 USA  
**USA Phone: (800)800-7496**  
Phone: (419)865-9497  
FAX: (419)865-9997  
www.ransom-randolph.com