



**An easy-to-use, phosphate-bonded investment that provides reliable performance.**

PC 15 investment is a phosphate investment for pressable ceramics.

Use with FastFire Liquid for optimal performance.

*PC 15 investment is formerly a Whip Mix product.*

## Features

- Provides reliable results with modern ceramic systems
- Fine-grained formula that captures exceptional detail

## Typical Material Properties\*

Liquid-to-Powder Ratio
27/100
Working Time
7-9 minutes
Set Expansion
1.0%
Thermal Expansion
0.7%
Compressive Strength
500 psi (3.4 MPa)

*\*These results are based on the testing methods, frequency and procedures of Ransom & Randolph or its approved suppliers. The levels referenced herein are only for general guidance and do not constitute a firm specification.*

## Availability

### PC 15 investment

100 grams (100 count).....38183

### FastFire Liquid

33.8 fl oz (1 L).....38161

11.5 fl oz (340 mL).....38166

To order, visit [Shop.Ransom-Randolph.com](http://Shop.Ransom-Randolph.com), contact your region's R&R Customer Service Team, or contact an authorized distributor. For a list of authorized distributors, visit [Ransom-Randolph.com/Distributors](http://Ransom-Randolph.com/Distributors).

D2P06 Rev. 2025-04-09