## Deluxcote® concentrate



#### Reduce Backup Coats – Withstand Process Stresses

Deluxcote concentrate was developed to reduce backup coats while building a shell that withstands the stresses of handling, dewax and pouring. Its unique formula is designed to build thicker, stronger and more flexible individual shell coats. Deluxcote concentrate is allowing foundries around the world to streamline their shell-building processes.

#### **Customer Testimonials**

- "We have 40% faster throughput with Deluxcote concentrate."
- "25% more parts go out the door."
- "We're using half as much patching materials as our previous shell required."
- "We've reduced a couple of coats and almost cut our robot cycle time in half."
- "We've increased shell room output and reduced shell room labor, saving about \$57,000 a year."

### Build a Stronger Shell with up to 50% Fewer Backup Coats

- Increase shell throughput and increase production without increasing labor or overhead costs.
- Reduce work in process inventory.
- Reduce shell room bottlenecks.
- Reallocate labor to other bottleneck areas.

#### Eliminate or Substantially Reduce Cracking

- Reduce scrap and rework related to shell cracking and defects like finning and inclusions.
- Reduce quantity of patching material required and labor time used to apply patch.
- Focus labor on pouring instead of shell reparation.
- Dramatically reduce or eliminate the need for a post-autoclave seal coat.

#### Use with a Wide Variety of Refractory Materials

- Benefits are available with your current refractory materials no need to make changes.
- Just add Deluxcote concentrate to Levasil® F0830 colloidal silica and water no other materials required.

Deluxcote concentrate is designed to give the investment caster numerous process & economic benefits through:

- Fewer dips per shell
- Better crack resistance, even with fewer coats
- Excellent wetting and draining properties
- Higher green strength
- Dry times similar to existing specialty binders
- Reduced material consumption

The actual benefits obtained by each foundry may vary depending on the particular foundry application and the critical process parameters that are targeted by each foundry.



# RANSOM & RANDOLPH

3535 Briarfield Boulevard | Maumee, OH 43537 USA 800.800.7496 | 419.865.9497 | 419.865.9997 (FAX) | www.ransom-randolph.com










# **DELUXCOTE®** CONCENTRATE

#### **Technical Data**

To illustrate the capabilities of binder made with Deluxcote concentrate, the green AFL measurement, in particular, demonstrates the versatility of the binder shell with Deluxcote concentrate versus existing high performance binders. At 4 coats, Deluxcote concentrate's shell has the same AFL as an existing high performance binder shell at 6 coats. Deluxcote concentrate's binder effectively completes the job with fewer coats.







### **Typical Material Properties\***

| Base Composition                                   | Colloidal Silica         |
|--|--------------------------|
| Other Composition                                  | Proprietary              |
| Total Solids Content (Including SiO <sub>2</sub> ) | 31.1%/weight             |
| Particle Size (Approximate)                        | 10 nm                    |
| pH at 77°F (25°C)                                  | 10.6                     |
| Specific Gravity                                   | 1.144                    |
| Weight/Volume                                      | 9.54 lbs/gal (1.14 kg/l) |
| Viscosity at 77°F (25°C)                           | <50 cps                  |
| Na <sub>2</sub> O Content (Weight)                 | 0.41%                    |
| Particle Charge                                    | Negative                 |
| Color  | White                    |

<sup>\*</sup>These results are based on the testing methods, frequency and procedures of Ransom & Randolph or its approved suppliers. The levels referenced herein are only for general guidance and do not constitute a firm specification.



## **RANSOM & RANDOLPH**



## Deluxcote® concentrate

#### **Formulations**

Due to the unique nature of the product, the formulation implemented will vary from foundry to foundry. This flexibility allows the foundry to obtain the maximum number of benefits from Deluxcote concentrate. The following formulation is for casters just starting out.

| Formula for 10 Gallo |                 |  |                         | r 10 Gallon                              | ns (lbs)           |                       | Formula for 10 Liters (kgs)     |   |                    |                       |                           |
|----------------------|-----------------|--|-------------------------|--|--------------------|-----------------------|---------------------------------|---|--------------------|-----------------------|---------------------------|
|                      | %<br>Refractory | Target<br>Slurry<br>Density (g/<br>ml) | Target<br>Viscosity     | Levasil®<br>F0830<br>colloidal<br>silica | Deionized<br>Water | Deluxcote concentrate | Ranco-Sil™<br>fused<br>silica** | Levasil<br>F0830<br>colloidal<br>silica | Deionized<br>Water | Deluxcote concentrate | Ranco-Sil<br>fused silica |
|                      | 61%             | 1.60-<br>1.64                          | 13-16<br>sec/#5<br>Zahn | 35.3                                     | 6.9                | 10.5                  | 82.4                            | 4.2                                     | 0.8                | 1.3                   | 9.9                       |

<sup>\*\*</sup>This formula can be used with Ranco-Sil 4 fused silica or Ranco-Sil 140 fused silica.

#### Application Recommendations

- 1. Remix the Deluxcote concentrate prior to use to ensure a homogeneous blend of material.
- 2. For best results, weigh all ingredients when making up a new slurry or making additions to an existing slurry.
- 3. When building the slurry, add the refractory last. If more than one refractory is used, add the lowest density refractory first: fused silicas (2.2 g/cc), aluminosilicates (2.7 g/cc), zircon (4.5 g/cc). Add refractory slowly for best results.
- 4. New and makeup slurries must be prepared with a propeller mixer, not in a rotating tank. This ensures proper dispersion of the refractory particles. The propeller mixer must be of adequate HP and RPM. Excessive mixing action can introduce air into the slurry and cause erratic viscosity and/or bubbles in the slurry coat.
- 5. As with any slurry, the viscosity of the slurry must be stable before use. A stable viscosity is one that does not change by more than 1 second when checked at 1 hour intervals. Viscosity can be increased by adding more refractory and decreased by adding more binder.
- 6. It is required to replace water lost to evaporation. When water is needed (based on test results for viscosity and/or binder solids), use distilled or deionized water as opposed to tap water, which can contain contaminants that can negatively affect slurry life.
- 7. Antifoam, wetting and bactericide agents are already formulated into Deluxcote concentrate and other additions may not be compatible. Contact R&R's technical team before making these additions to the slurry.

#### Slurry Control Procedures

Slurry Control Worksheets are available for download at www.ransom-randolph.com. Slurry Control Worksheets allow you to input data directly and help you calculate values.

#### Slurry Testing Frequency

R&R recommends running the following tests accordingly.

| Slurry Test       | Recommended Testing Frequency |
|-------------------|-------------------------------|
| Slurry Viscosity  | Two Times Per Shift           |
| Slurry Density    | Weekly                        |
| Refractory Solids | Weekly                        |
| Binder Solids     | Two Times Per Week            |
| Binder pH         | Weekly                        |



## RANSOM & RANDOLPH

3535 Briarfield Boulevard | Maumee, OH 43537 USA 800.800.7496 | 419.865.9497 | 419.865.9997 (FAX) | www.ransom-randolph.com







# DELUXCOTE® CONCENTRATE

### **Target Binder Solids Range**

The target binder solids range for Deluxcote concentrate is 29.5-31.5% by weight.

| Specific Gravity | Binder Solids | Specific Gravity | Binder Solids | Specific Gravity | Binder Solids |
|------------------|---------------|------------------|---------------|------------------|---------------|
| 1.126            | 27.3          | 1.142            | 29.5          | 1.158            | 31.7          |
| 1.127            | 27.4          | 1.143            | 29.6          | 1.159            | 31.8          |
| 1.128            | 27.6          | 1.144            | 29.7          | 1.160            | 31.9          |
| 1.129            | 27.7          | 1.145            | 29.9          | 1.161            | 32.1          |
| 1.130            | 27.8          | 1.146            | 30.0          | 1.162            | 32.2          |
| 1.131            | 28.0          | 1.147            | 30.2          | 1.163            | 32.3          |
| 1.132            | 28.1          | 1.148            | 30.3          | 1.164            | 32.5          |
| 1.133            | 28.2          | 1.149            | 30.4          | 1.165            | 32.6          |
| 1.134            | 28.4          | 1.150            | 30.6          | 1.166            | 32.8          |
| 1.135            | 28.5          | 1.151            | 30.7          | 1.167            | 32.9          |
| 1.136            | 28.7          | 1.152            | 30.8          | 1.168            | 33.0          |
| 1.137            | 28.8          | 1.153            | 31.0          | 1.169            | 33.2          |
| 1.138            | 28.9          | 1.154            | 31.1          | 1.170            | 33.3          |
| 1.139            | 29.1          | 1.155            | 31.3          | 1.171            | 33.4          |
| 1.14             | 29.2          | 1.156            | 31.4          | 1.172            | 33.6          |
| 1.141            | 29.3          | 1.157            | 31.5          | 1.173            | 33.7          |

### Safety

OSHA-approved respiratory protection should always be worn to avoid inhalation of respirable silica dust, which can result in an irreversible lung disease, silicosis. Such exposure includes slurry makeup, casting, knockout and cleanup. Refer to SDS for specific details.

#### Storage & Handling

Keep from freezing. Deluxcote concentrate must be maintained above 35°F (2°C) to prevent the material from precipitating irreversibly and making the product unsuitable for use. Binder stored in transparent or translucent containers should be sheltered from direct sunlight. Shelf life is 1 year from date (MMDDYY) in batch lot number on label. Rotate stock to maximize shelf life.

#### **Technical Tips**

For additional information and recommendations, refer to the Shell Building, Slurry Control, Autoclaving and FlashFire Dewax Method Technical Tips available for download at www.ransom-randolph.com.



## **RANSOM & RANDOLPH**

3535 Briarfield Boulevard | Maumee, OH 43537 USA 800.800.7496 | 419.865.9497 | 419.865.9997 (FAX) | www.ransom-randolph.com





# **DELUXCOTE®** CONCENTRATE

As the conditions or methods of use are beyond our control, we do not assume any responsibility and expressly disclaim any liability for any use of this product. Information contained herein is believed to be true and accurate but all statements or suggestions are made without warranty, expressed or implied, regarding accuracy of the information, the hazards connected with the use of the material or the results to be obtained from the use thereof. Compliance with all applicable federal, state, and local regulations remains the responsibility of the user. All potential liability related to the sale and use of this product is limited to the cost of the particular goods sold in their respective transactions.



Issue Date: July 23, 2023