

R&R ROSIN DIPS



R&R Rosin Dips are ideal for partial denture refractory models. They offer a low melting point of 250 °F (121 °C).

R&R Rosin Dips are available in two formulas:

- R&R Rosin Dip
 - A standard rosin dip.
- R&R Rosin Dip Hard
 - An extra hard rosin dip that holds the corners of the preps better and is less prone to chipping, reducing remakes or excessive grinding to seat the frame.

Typical Material Properties*

	R&R Rosin Dip	R&R Rosin Dip Hard
Melting Point	250 °F (121 °C)	250 °F (121 °C)
Color	Yellow	White

*These results are based on the testing methods, frequency and procedures of Ransom & Randolph or its approved suppliers. The levels referenced herein are only for general guidance and do not constitute a firm specification.

Application Instructions

1. Place the model in a model drying oven at 450 °F (232 °C) for at least 1 hour.
2. Remove the model from the oven and immediately submerge it into rosin dip for approximately 8-10 seconds.
3. The rosin dip should be at a temperature of 250 °F (121 °C).
4. Remove the model from the rosin dip and place the model on its heels or posterior section to allow for cooling and drainage prior to waxing.

As the conditions or methods of use are beyond our control, we do not assume any responsibility and expressly disclaim any liability for any use of this product. Information contained herein is believed to be true and accurate but all statements or suggestions are made without warranty, expressed or implied, regarding accuracy of the information, the hazards connected with the use of the material or the results to be obtained from the use thereof. Compliance with all applicable federal, state, and local regulations remains the responsibility of the user. All potential liability related to the sale and use of this product is limited to the cost of the particular goods sold in their respective transactions.



RANSOM & RANDOLPH

3535 Briarfield Boulevard, PO Box 1570 | Maumee, OH 43537 USA
800.253.4502 | 419.865.9497 | 419.865.9997 (FAX) | www.ransom-randolph.com



Issue Date: November 29, 2021

Investing with Innovation™